

## Silicone Aluminium

**PRODUCT DESCRIPTION** A one pack, aluminium pigmented silicone resin coating.

**INTENDED USES** As a light reflective primer/finish for surfaces that can reach dull red heat of up to 540°C, such as exhaust stacks. For use at Newbuilding, Maintenance & Repair or On Board Maintenance.

**PRODUCT INFORMATION**

|                               |  |
|-------------------------------|--|
| <b>Colour</b>                 | HTA097-Aluminium, HTA099-Black   |
| <b>Finish/Sheen</b>           | Gloss  |
| <b>Part B (Curing Agent)</b>  | Not applicable   |
| <b>Volume Solids</b>          | 45% (ISO 3233:1998)  |
| <b>Typical Film Thickness</b> | 25 microns dry (56 microns wet)  |
| <b>Theoretical Coverage</b>   | 18 m <sup>2</sup> /litre at 25 microns dft, allow appropriate loss factors |
| <b>Method of Application</b>  | Airless Spray, Brush, Conventional Spray, Roller                           |
| <b>Flash Point (Typical)</b>  | Single Pack 25°C   |

| <b>Drying Information</b>                 | 5°C                          |     | 15°C    |     | 25°C    |     | 35°C    |     |
|---|------------------------------|-----|---------|-----|---------|-----|---------|-----|
| Touch Dry [ISO 9117/3:2010]               | 90 mins                      |     | 60 mins |     | 30 mins |     | 15 mins |     |
| Hard Dry [ISO 9117-1:2009]                | 5 hrs                        |     | 3 hrs   |     | 2 hrs   |     | 60 mins |     |
| <b>Overcoating Data - see limitations</b> | <b>Substrate Temperature</b> |     |         |     |         |     |         |     |
|   | 5°C                          |     | 15°C    |     | 25°C    |     | 35°C    |     |
| <b>Overcoated By</b>                      | Min                          | Max | Min     | Max | Min     | Max | Min     | Max |
| Intertherm 50                             | 24 hrs                       | ext | 16 hrs  | ext | 12 hrs  | ext | 6 hrs   | ext |

**REGULATORY DATA**

|            |  |
|------------|--|
| <b>VOC</b> | 495 g/lit as supplied (EPA Method 24)<br>509 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC) |
|------------|--|

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

## Silicone Aluminium

### CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (Exova Warringtonfire)
- Fire Resistance - Marine Equipment Directive compliant

Consult your International Paint representative for details.

---

### SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

---

### SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

### NEWBUILDING

Intertherm 50 is suitable for application to steelwork freshly coated with zinc silicate shop primers.

If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Ensure that the zinc primer is fully cured prior to the application of Intertherm 50 by following the curing instructions on the relevant product data sheet. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:2007).

### MAJOR REFURBISHMENT

Abrasive blast clean to Sa2½ (ISO 8501-1:2007).

### REPAIR/OBM

Intertherm 50 may be applied directly over aged Intertherm 50 following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to a firm edge and Intertherm 50 or an appropriate primer should be used to repair the area before application of the full coat.

Consult your International Paint representative for specific recommendations.

### NOTE:

**For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

## Silicone Aluminium

### APPLICATION

|                                   |   |
|-----------------------------------|---|
| <b>Mixing</b>                     | This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.   |
| <b>Thinner</b>                    | Not recommended. Use International GTA007 only in exceptional circumstances. DO NOT thin more than allowed by local environmental legislation.  |
| <b>Airless Spray</b>              | Recommended.<br>Tip Range 0.33-0.43 mm (13-17 thou)<br>Total output fluid pressure at spray tip not less than 112 kg/cm <sup>2</sup> (1590 p.s.i.)  |
| <b>Conventional Spray</b>         | Gun DeVilbiss MCB or JGA<br>Air Cap 704 or 765<br>Fluid Tip E   |
| <b>Brush</b>                      | Recommended.  |
| <b>Roller</b>                     | Recommended.  |
| <b>Cleaner</b>                    | International GTA007  |
| <b>Work Stoppages and Cleanup</b> | Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.   |
| <b>Welding</b>                    | In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting." |

### SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

#### **EMERGENCY CONTACT NUMBERS:**

**USA/Canada - Medical Advisory Number 1-800-854-6813**

**Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191**

**China – Contact (86) 532 83889090**

**R.O.W. - Contact Regional Office**

## Silicone Aluminium

### LIMITATIONS

Intertherm 50 is not suitable for exposure in acid or alkaline conditions.

Do not over apply. Application above 40 microns dft will result in blistering when subject to high temperatures.

Excessive dry film thickness may result in cracking. Dry film thickness must not exceed 25 microns.

Up to 3 coats at a maximum of 25 microns per coat can be applied without the requirement of heating between coats. This provides maximum corrosion protection when it is not possible to use a zinc silicate priming system.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

| UNIT SIZE | Unit Size  | Part A     |          |
|-----------|------------|------------|----------|
|           |            | Vol        | Pack     |
|           | 4.8 lt     | 4.8 lt     | 5 lt     |
|           | 5 US gal   | 5 US gal   | 5 US gal |
|           | 0.8 US gal | 0.8 US gal | 1 US gal |

For availability of other unit sizes consult International Paint

| UNIT SHIPPING WEIGHT (TYPICAL) | Unit Size  | Unit Weight |
|--------------------------------|------------|-------------|
|                                | 4.8 lt     | 5.86 Kg     |
|                                | 5 US gal   | 50.5 lb     |
|                                | 0.8 US gal | 8.3 lb      |

| STORAGE | Shelf Life | 12 months minimum at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. Prevent the ingress of moisture as this may lead to a pressure build up in the container. |
|---------|------------|---|
|         |            |   |

**WORLDWIDE AVAILABILITY** Consult International Paint.

### IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2015

[www.international-marine.com](http://www.international-marine.com)