

DULUX TRADE BONDING LIQUID

TECHNICAL DATA SHEET

Version 1 – 2017 SEPTEMBER

THIS ISSUE SUPERSEDES ALL PREVIOUS PUBLICATIONS

PRODUCT DESCRIPTION

Sealer for penetrating and bonding powdery surfaces.

PRODUCT USES

- Recommended as a penetrating primer or sealer for new dry interior and exterior porous surfaces such as gypsum plaster, brick, concrete, cement and composite boarding. Normally used when top coated with filler coats and Eggshell or Gloss Enamel paints.
- Suitable as a bonding liquid for penetrating and binding unsound previously painted substrate.

FEATURES AND BENEFITS

- For interior and exterior use.
- One product convenience.
- Contains high quality resin. The best possible penetration and bonding of powdery surfaces - ensures surfaces are properly prepared for subsequent topcoats - thus prolonging life span of the total paint system.
- Excellent alkali resistance so that it can be used on new plaster.
- Easy to apply with brush and roller.
- Can be over-coated with water and solvent based topcoats.

PRODUCT INFORMATION

Appearance	Matt to Semi-Gloss
Colour	Clear
Density at 23°C	Approx. 0.80Kg/L
Solids Content	By weight: Approx. 19% By volume: Approx. 15%
Packaged Viscosity	Viscosity at 23°C: Approx. 15 seconds F4
Spreading Rate	Approx. 12m ² per litre depending on surface porosity, profile and application method
Recommended DFT per coat	Penetrates substrate
Flash Point	37°C

DULUX TRADE BONDING LIQUID

APPLICATION INFORMATION

Mixing	Stir until homogeneous with a flat paddle
Application Surface conditions	Surface Temperature between 10 - 35°C Relative Humidity between 10 - 85 % OR 2°C above dew point minimum.
Application methods	Brush, roller or spray application. Brush or roller preferred to ensure the product is worked well into the surface.
Thinner	Thinning not recommended. Ready for use after thorough stirring for brush and roller applications. Mineral Turpentine if required for spraying to maximum of 5 - 10% of product volume.
Drying Time	Surface dry 2 hours at 23°C.
Recoating Time	4 hours 23°C maximum (Drying times will be extended during cold, wet or humid conditions)
Cleaning of equipment	After use, remove as much product as possible, and then clean immediately with Dulux Pre-Paint Brush Cleaner Degreaser or Mineral Turpentine.
Substrates	Suitable for cement plaster, gypsum plaster, concrete, friable masonry, porous bricks, fibre cement and composite boarding
Precautions:	Do not apply during cold (below 10°C) or wet weather. Not suitable as a primer for metal surfaces. Surfaces must be completely dry before applying this material. If the Dulux Trade Bonding Liquid application produces a glossy finish, lightly sand to a matt finish. Not designed to withstand natural weathering. It should be over coated within 48 hours.
Coats Required	New work 1 coat, a 2 nd coat may be required on very absorbent surfaces
Top Coating	Can be over coated with most Dulux decorative finishes.

SURFACE PREPARATION

Plaster sand should comply with SABS 1090 requirements. Plaster mix must be applied at a minimum thickness of 10mm, curing to a hard and sound finish, free of soft and friable material. MPA strength must comply with SABS 0164-1 (10MPa=2, 6:1 and 5MPa=4:1). Ensure that surfaces are sound and free from dust, oil, grease, dirt, and debris. Surfaces must be thoroughly dry - no more than 12% moisture content.

DULUX TRADE BONDING LIQUID

SURFACE PREPARATION

NEW SURFACES

Cement plaster, Gypsum Plaster, Concrete, Porous Cement Brick, Fibre Cement and Composite boarding

- It is recommended that fresh plaster should be allowed one week drying for every 5mm thickness; and longer in cold or damp weather.
- Spot-prime metal strips and nail heads with appropriate metal primer.
- Apply a single coat **Dulux Trade Bonding Liquid**.
- For very absorbent surfaces such as gypsum plaster wipe a black cloth over the dried single coat **Dulux Trade Bonding Liquid** applied and if a white residue is found on the back of the cloth apply 1 to 2 further coats of **Dulux Trade Bonding Liquid** to achieve correct binding and sealing properties.

Cement and Fibre Cement Roof Tiles (new)

- To remove dust, debris and chalky residue, wash the entire roof area using high-pressure washing, using a rotating nozzle at a pressure between 150 and 200 Bar. Alternatively, scrub the entire roof area with a bristle brush, using water from a garden hose and allow drying.

Cement and Fibre Cement Roof Tiles (weathered, unpainted)

- To remove dust, debris and chalky residue from cement roof tiles, wash the entire roof area using high-pressure washing, using a rotating nozzle at a pressure between 150 and 200 Bar. Alternatively, scrub the entire roof area with a bristle brush, using water from a garden hose.
- Old, weathered fibre cement is porous and may encourage the growth of fungus. Scrub these areas with either of the following solutions: 25% chlorine solution and water or 25% sodium hypochlorite and water solution. Rinse off thoroughly, removing residues of the cleaning solution, and at the same time cleaning off dust and debris from the roof.

PREVIOUSLY PAINTED SURFACES

Old Paint in Poor Condition

- Remove all loose and flaking paint.
- Friable surfaces must be removed and repaired.
- Mould instructions. To kill lichen and algae growth, scrub with one of the following solutions: either 4:1 water/chlorine, or 4:1 water/sodium hypochlorite. Ensure that the areas are completely saturated, and allow the solution to react for a minimum of 4 hours. Rinse the complete wall surface thoroughly with clean water.
- Chalked, powdery surfaces must be thoroughly brushed or washed down.

DULUX TRADE BONDING LIQUID

SURFACE PREPARATION

PREVIOUSLY PAINTED SURFACES

Lime Washed and Distempered Surfaces

- Surfaces must be thoroughly wire-brushed, scraped and sanded to remove all lime wash i.e. until the underlying plaster or brickwork is visible, known as the “grey state”.
- Remove distemper, with hot water and scraping. Wash surfaces thoroughly with **Dulux Pre-Paint Sugar Soap** solution and rinse with clean water. Allow surfaces to dry out thoroughly.
- Apply a single coat **Dulux Trade Bonding Liquid**. For very absorbent surfaces such as lime wash, two coats may be required. The first coat must be thinned 20% with Mineral Turpentine for penetration.

Cement and Fibre Cement Roof Tiles

- Perform adhesion tests on the existing coating to cross cut test ISO 2409-2013 standards
- To remove dust, debris and chalky residue and loose paint from cement roof tiles, wash the entire roof area using high-pressure washing, using a rotating nozzle at a pressure between 150 and 200 bar. Alternatively, scrub the entire roof area with a bristle brush, using water from a garden hose. Cement and Fibre Cement Roof Tiles in poor condition, strip completely.
- Old, weathered fibre cement is porous and may encourage the growth of fungus. Scrub these areas with either of the following solutions: 25% chlorine solution and water or 25% sodium hypochlorite and water solution. Rinse off thoroughly, removing residues of the cleaning solution, and at the same time cleaning off dust and debris from the roof.

FILLING

Fill all imperfections with the appropriate Dulux Pre-Paint filler and spot prime filled areas with **Dulux Trade Bonding Liquid** once the crack filler has dried properly. Failure to do this will result in uneven sheen levels between the repaired and normal areas.

DULUX TRADE BONDING LIQUID

HEALTH AND SAFETY INFORMATION

Solvent based paints are flammable.

This product contains no added lead. Avoid contact with skin or eyes. Keep out of reach of children. If accidentally swallowed, seek medical advice immediately and show this container to the doctor.

Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding should be used wherever possible.

If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used. Do not empty into drains or watercourses.

Ensure good ventilation during application and drying. It is recommended to use suitable protective clothing and equipment. To avoid the risk of spillage, always store and transport containers in a secure upright position. Refer to Material Safety Data Sheet for complete information.

ADDITIONAL INFORMATION

Packaging	5Lt, 20Lt
Storage Conditions	Store under cool dry conditions away from direct sunlight, heat and extreme cold.
Disclaimers	N/A product specific

TDS STD DISCLAIMER

The recommendations contained herein are given in good faith and meant to guide the specifier or user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Dulux control.

Important Note; Technology may change with time, necessitating changes to this Technical Data Sheet (TDS).

It is the responsibility of the user to ensure that the latest TDS is being used for reference. Dulux Technical Data Sheets are available on our website www.duluxtrade.co.za or please contact: Dulux On-Line on 0860 330 111. Email ZA.Helpline@akzonobel.com

ICI Dulux (Pty) Ltd is part of AkzoNobel. ICI Dulux (Pty) Ltd Reg No.1946/020769/07